

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup> :

B01D 15/08

A1

(11) International Publication Number:

WO 94/26381

(43) International Publication Date: 24 November 1994 (24.11.94)

(21) International Application Number: PCT/US94/05532

(22) International Filing Date: 17 May 1994 (17.05.94)

(30) Priority Data:

08/062,134

17 May 1993 (17.05.93)

US

08/155,001

19 November 1993 (19.11.93)

US

(71) Applicant: MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02138 (US).

(72) Inventors: TANAKA, Toyochi; 22 Lowell Road, Wellesley, MA 02181 (US). ANNAKA, Masahiko; Room 207, 43-2, Tana-cho, Midori-ku, Yokohama 227 (JP). MASAMUNE, Satoru; 182 Brookline Street, Newton, MA 02159 (US).

(74) Agent: KAPLAN, Warren; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).


(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

*With international search report.*

*Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.*

(54) Title: ARTIFICIAL RECEPTORS, ANTIBODIES, AND ENZYMES



(57) Abstract

Multiple-phase transition copolymers (14) are formed which can selectively bind and release a chemical (12), or which can selectively catalyze a specific chemical reaction.

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

ARTIFICIAL RECEPTORS, ANTIBODIES, AND ENZYMESBackground of the Invention

Receptors, antibodies, and enzymes have a common ability to selectively bind molecules. However, known receptors, antibodies, and enzymes have only a limited capacity for manipulation to control binding and, possibly, release of the molecules or products formed from the bound molecules.

Therefore, a need exists for artificial receptors, antibodies, and enzymes which overcome or minimize the above-mentioned problems.

Summary of the Invention1. Proteins: Polymers with Structure and Function

Proteins are linear chain molecules in which twenty kinds of amino acids are connected in specific sequences. They can fold into unique structures and perform various sophisticated functions and serve as molecular receptors to receive molecular messages, antibodies to recognize alien molecules and cells, and enzymes that catalyze biochemical reactions. They are the key molecules to maintain life. General principles are not known, however, with which to design and synthesize such polymers that can form structures and function like proteins. The current biotechnology depends on the biological systems and biological information as given in the DNA sequences obtained from biological cells.

If such general principles are known, it will be possible to design and synthesize polymers that will have

-2-

functions similar to proteins. More specifically, polymers may be synthesized that can specifically bind target molecules and release them upon their conformational changes, or polymers that can catalyze chemical reactions.

## 2. Theories on Unique Structure of Heteropolymers

The sequence of amino acids was considered to be essential for the protein to have a particular structure and exercise specific functions. Recent theoretical studies have shown, however, that for a polymer to fold into a unique structure the polymer does not have to have a specific sequence, but the composition of the monomers that construct the polymer has to satisfy a compositional requirement (Shachnovich & Gutin (1989)). The requirement for a composition is practically infinitely easier than the requirement of a sequence. Of course, the structures are usually different for different sequences, but whether or not a polymer can fold into a unique, thermodynamically stable structure depends only on the composition of the constituent monomers.

For a polymer to have a molecular recognition capability, structural requirement is imposed only on the active site area where monomers should be arranged in such a way that they fit perfectly to the target molecule. The other portion of the polymer must have a stable structure, but the structure can be any one.

-3-

Therefore, except for the active site, polymers can be made by using a proper composition of monomers without specifying the sequence. As we shall see later, the active site configuration can be created by method  
5 molecular imprinting.

### 3. Discovery of Multiple Phases of Heteropolymer Gels

Until now no synthetic polymers were known to have such a stable state, similar to that of proteins. We  
10 have recently discovered that a synthetic polymer can have stable phases with possibly discrete structures, and undergo discontinuous phase transition between these stable phases (Annaka & Tanaka (1992)). A necessary condition is that the polymer be made of random  
15 copolymers whose segments are interacting with repulsive as well as attractive forces. The attractions have to be a combination of hydrogen bonding and one or more of the other fundamental biological interactions, such as van der Waals, hydrophobic, and electrostatic (between plus  
20 and minus charges) interactions (Tanaka and Annaka (1993)). A proper composition of these forces is required for the achievement of the new phases.

### 4. Method of Molecular Imprinting

25 Another important development is the method of molecular imprinting to create polymers that are capable of recognizing target molecules (Wulff, Mösbach, Shea).

-4-

In these methods, highly crosslinked plastics is formed in the presence of target molecules. When the target molecules are washed away, there remain holes that fit to the target molecules. In this case the stability is  
5 obtained by highly cross-linking density rather than by the cooperative monomer-monomer interactions as in the case of proteins.

Based on these findings we have devised a generic method to synthesize copolymers that are capable of  
10 molecular recognition (artificial antibodies) or catalytic activities (artificial enzymes).

#### Artificial Antibodies

The present invention relates to a method of forming  
15 a multiple-phase transition copolymer which can selectively bind a substrate, and release the substrate upon undergoing volume phase transition. The invention also relates to multiple-phase transition copolymers which are formed by the method of invention. Such  
20 polymers will have specific molecular recognition, absorption and recovery of the substrate.

In one embodiment, the method includes forming a monomer solution, which, upon polymerization, will form a copolymer get which exhibit multiple-phase transition at  
25 a plurality of phase transition conditions. Prior to polymerization the template molecules, which are the substrate or substrate analogues, are added to the

-5-

5 solution. The combined monomer solution and template are exposed to condition sufficient to cause the monomer solution to polymerize and form the copolymer. The copolymer is then brought to an expanding phase transition by varying temperature, solvent or other parameters, so that the templates are washed away from the copolymers. The copolymers are then exposed to a change in environmental conditions, such as temperature or solvent, to return to the original stable state. Such  
10 copolymers will show the specific binding of the substrate molecules.

#### Artificial Enzymes

15 The present invention relates to a method of forming a multiple-phase transition copolymer which can selectively catalyze a substrate, and release the product(s) upon undergoing volume phase transition. The invention also relates to multiple-phase transition copolymers which are formed by the method of invention.  
20 Such polymers will have specific catalytic activity upon a substrate and recovery of the products into which the substrate is converted.

25 In one embodiment, the method includes forming a monomer solution which, upon polymerization, will form a copolymer gel which exhibit multiple-phase transition at a plurality of phase transition conditions. Prior to polymerization the template molecules mimicking the

-6-

substrate in its transition state are added to the solution. Enzymes are known to recognize its substrate in its transition state into the products. Such mimicking molecules have been developed for various substrates. The combined monomer solution and template are exposed to conditions sufficient to cause the monomer solution to polymerize and form the copolymer. The copolymer is then brought to an expending phase transition by varying temperature, solvent and other parameters, so that the templates are washed away from the copolymers. The copolymers are then exposed to a change in environmental conditions, such as temperature or solvent, to return to the original stable state. Such polymers will have specific catalytic activity upon a substrate and recovery of the products into which the substrate is converted.

The advantage of this invention include formation of phase transition copolymers which can selectively bind a substrate or can carry out selective catalytic conversion of a substrate into products. The copolymers can be manipulated through phase transitions to absorb substrates and release substrates or products which are formed during conversion of the substrates. The copolymers, thus formed, will be able to mimic the operation of chemical receptors, antibodies, and enzymes.



-7-

Brief Description of the Figures

Figures 1A through 1D represent steps of one embodiment of a method of forming the multiple-phase transition copolymers of the invention.

5        Figures 2A through 2F represent steps of an alternate method of forming the multiple-phase transition copolymers of the invention.

Detailed Description of the Invention

10        The features and other details of the phase-transition copolymers and methods of forming the phase-transition copolymers will now be more particularly described and pointed out in the claims. It will be understood that the particular embodiments of the  
15        invention are shown by way of illustration and not as limitations of the invention. The principle features of this invention can be employed in various embodiments without departing from the scope of the invention.

      "Phase-transition" of gels, as that term is used  
20        herein, means a discontinuous volume change of gels between an extended phase and a more contracted phase or vice-versa. "Phase-transition gels," as that term is used herein, are gels which exhibit a phase transition at a phase-transition condition. The difference in volume  
25        between the expanded and the contracted phase of the phase-transition gels can be as large as many thousands of times. Examples of phase-transition gels are

-8-

disclosed in Tanaka et al., U.S. Patent No. 4,732,930 and U.S. Patent Application Serial Numbers 07/425,788, 07/470,977, 07/558,733, and 07/720,187, the teachings of which are incorporated herein by reference.

5 "Multiple-phase transition gels," as that term is used herein, means gels which can exhibit phase transitions at a plurality of distinct phase-transition conditions. For example, a multiple-phase transition gel or copolymer could exhibit an expanding phase transition  
10 by lowering the temperature of the gel at a first temperature and, after the first expanding phase transition and continued lowering of temperature, exhibit a second expanding phase transition at a lower temperature than that at which the first expanding phase  
15 transition occurred.

Examples of multiple-phase transition gels are described in Annaka and Tanaka, *Nature* 355 (6359):430-432 (1992), the teachings of which are incorporated herein by reference.

20 In one embodiment, the method includes forming a multiple-phase transition copolymer or gel which can selectively bind a substrate. A monomer solution is formed which, upon polymerization, will form a copolymer gel that can exhibit phase transition at a plurality of  
25 distinct phase-transition conditions. As shown in Figures 1A and 1B, monomer 10 of a monomer solution is combined with template 12 which, upon polymerization of

-9-

monomer 10, will cause the resulting copolymer to selectively bind the substrate. Template 12, in effect, mimics the configuration of the substrate to which the resulting copolymer will selectively bind. The combined  
5 monomer solution and template 12 are exposed to conditions sufficient to cause the monomer solution to polymerize and form copolymer 14, which is shown in Figure 1B. At least a portion of copolymer 14 forms at template 12 so that copolymer 14 is selectively  
10 configured for binding a chemical having the same or a similar chemical structure. Optionally, copolymer 14 is then ionized in an amount sufficient to cause copolymer 14 to exhibit a plurality of phase transitions upon exposure to distinct phase-transition conditions.

15 Copolymer 14 is then exposed to conditions sufficient to cause copolymer 14 to exhibit an expanding phase transition, thereby releasing template 12 from copolymer 14, as shown in Figure 1C. Phase transition conditions at which the copolymers exhibit a  
20 discontinuous volume change can include physical conditions, chemical conditions, or combinations of physical and chemical conditions. Examples of physical phase-transition conditions include: temperature; electromagnetic radiation, such as infrared energy,  
25 visible light and ultraviolet lights; etc. Examples of chemical phase-transition conditions include: concentration of ionic species, such as hydrogen and

-10-

water, i.e., pH: cross-linking agents, such as cross-linking agents which crosslink the copolymer network; inorganic and organic solvents; specific chemicals; etc. Phase-transition conditions at which copolymers exhibit a discontinuous volume change can also include combinations of physical conditions, combinations of chemical conditions, or combinations of physical and chemical conditions.

Copolymer 14 is then separated from template 12 by a suitable method, such as immersing and flushing with a large amount of water. When the copolymers are crosslinked in a form of a gel, the gel can be very easily washed. When the copolymers are not crosslinked, a dialysis bag are used to wash the copolymers.

The copolymers will then be returned to the original state by reversing the physical or chemical or combined conditions to the original condition. The copolymers will then have active sites that specifically bind the substrate.

The same procedure applies to synthesis of artificial enzymes. In this case we use as target molecules, molecules that mimic the transition state of substrate. The actual transition state of substrate is unstable. Many molecules have been recently synthesized that mimic the transition state of substrate, but stable.

In an alternate method, shown in Figures 2A through 2F, monomer 18 of a monomer solution is formed which,

-11-

upon polymerization, will form a copolymer that can exhibit phase transitions at a plurality of distinct phase-transition conditions. The monomer solution is combined with phase-transition gel 20 to which template 22 is bound, such as by covalent chemical bonds. The combined monomer solution and phase-transition gel 20 are exposed to conditions sufficient to cause the monomer solution to polymerize in gel 20 and form copolymer 24. A portion of the copolymer 24 forms at the template 22 and is thereby bound to phase-transition gel 20 by template 22, as shown in Figure 2C.

As shown in Figure 2D, phase-transition gel 20 and copolymer 24 are then exposed to conditions sufficient to cause gel 20 to exhibit a contracting phase transition that causes copolymer 24 which is not bound to template 22 to be discharged from gel 20. Discharged copolymer 24 is then washed from gel 20. Gel 20 is subsequently exposed to conditions sufficient to cause gel 20 to exhibit an expanding phase transition and to conditions sufficient to cause copolymer 24 to exhibit a phase transition that releases copolymer 24 from template 22, as shown in Figure 2E. Gel 20 is subsequently exposed to conditions that cause gel 20 to exhibit a contracting phase transition, whereby released copolymer 24 is discharged from gel 20, as shown in Figure 2F.

In a particularly preferred embodiment, the phase transition gel to which the template is bound is poly(N-

-12-

isopropylacrylimide). A preferred copolymer is acrylic acid/N-isopropylacrylimide/methacrylamidopropyl-ammonium-chloride (MAPTAC). In one embodiment, the monomer solution includes 440 mM of acrylic acid, 240 mM of MAPTAC, 20 mM of N-isopropylacrylimide, 0.133 grams of N,N'-methylene bisacrylamide (cross-linker), 40 mg of ammonium chloride and 100 ml of water. The monomer solution can be polymerized to form a suitable copolymer by heating the solution to about 60°C.

Examples of suitable templates include ethyl- $\beta$ -fluoro- $\beta$ -(p-nitrophenyl)propionate, such as is commonly used for hydrogen fluoride elimination, and p-nitrophenyl glutarate half ester, such as can be employed for ester hydrolysis.

The method for selectively binding a substrate for conversion of the substrate to a product includes combining a substrate with a copolymer, such as described above, which can bind a substrate by exposing the copolymer and the substrate to conditions which cause the copolymer to exhibit a contracting phase transition. The combined substrate and copolymer are then exposed to conditions which cause the copolymer to exhibit a first contracting phase transition, whereby the substrate is selectively bound to the copolymer. The bound substrate is then exposed to conditions which cause catalytic or enzymatic conversion of the substrate to the product. The copolymer can then be exposed to a phase-transition

-13-

condition which causes the copolymer to exhibit a second contracting phase transition while the substrate is in a transition state, during the enzymatic conversion to the product.

5       The copolymer and the resulting product are then exposed to conditions which cause the copolymer to exhibit an expanding phase transition that releases the product.

10       Monomer Composition

          The criterion for a proper composition is that the copolymers as prepared in one of its multiple phases. The monomer should be capable of interacting through hydrogen bonding, repulsive or attractive Coulombic  
15       interactions, hydrophobic interaction, and/or van der Waals forces. The criterion for a proper composition is that the copolymers as prepared in one of its multiple phases.

          In a particularly preferred embodiment, the  
20       composition for the multiple-phase transition copolymer gel is;

	methacrylic acid (capable of	0.5 mole
	hydrogen bonding and ionization)	
25	dimethylacrylamide (capable of	0.5 mole
	hydrogen bonding)	
	N-isopropylacrylamide (capable of	1.0 mole

-14-

hydrophobic interaction)

	Silver salt of acrylamidopropylsulfonic acid	0.5
	mole	
5	N,N'methylene-bis-acrylamide	8.6 mole
	(crosslinker)	
	ammonium persulfate (polymerization	1.76 mole
	initiator)	
	water	1.0 mole
10	template	30 mole

The concentrations of monomer components are given as relative proportions. The monomer solution can be polymerized to form a suitable copolymer by heating the solution to approximately 60°C for approximately 2 hours.

15 The gel thus synthesized can be washed with generous amounts of an aqueous solution of sodium hydroxide, pH 10. The gel becomes fully expanded in this solution.

The gel can then be placed in an aqueous solution of approximately 0-30 mM template molecules, the solution having a pH within the range of approximately 3 to 6. The gel will shrink in this solution and will bind target molecules.

20 Molecules such as rhodamine B, 9 ethyladenine, or tyrosine can be used as template and/or as target molecules.

25



-15-

References

1. Shakhnovich, E.I. and Gutin, A.M., *Europhys. Lett.*,  
8, 327-332 (1989).
2. Annaka, M. and Tanaka, T., *Nature*, 349, 400-401  
5 (1991).
3. Tanaka, T. and Annaka, M., *J. Intelligent Material  
Systems and Structures*, 4, 549-552 (1993).
4. Tanaka, T., Fillmore, D.J., Sun, S.-T., Nishio, I.,  
Swislow, G., and Shah, A., *Phys. Rev. Lett.*, 45,  
10 1636-1639 (1980).
5. Ilmain, F., Tanaka, T., and Kokufuta, E., *Nature*,  
349, 400-401 (1991).
6. Kempe, M., Fischer, L., and Mosbach, K., *Journal of  
Molecular Recognition*, 6, 25-29 (1991).
- 15 7. Wulff, G., *Am. Chem. Soc. Symp. Series*, 308, 186-230  
(1986).

Equivalents

Those skilled in the art will recognize, or be able  
20 to ascertain using no more than routine experimentation,  
many equivalents to the specific embodiments of the  
invention described specifically herein. Such  
equivalents are intended to be encompassed in the scope  
of the following claims.

-16-

CLAIMS

What is claimed is:

- 5        1.    A method of forming a multiple phase transition  
         copolymer which can selectively bind a substrate,  
         comprising the steps of:
- 10           a)    forming a monomer solution which, upon  
                 polymerization, will form a copolymer that can  
                 exhibit phase transition at a plurality of  
                 distinct phase-transition conditions;
- 15           b)    combining the monomer solution with a template  
                 which, upon polymerization of the monomer  
                 solution, will cause the resulting polymer to  
                 specifically bind said substrate; and
- 20           c)    exposing the combined monomer solution and  
                 template to conditions sufficient to cause the  
                 monomer solution to polymerize and form said  
                 copolymer.
- 25        2.    A method of Claim 1, further including the step of  
         exposing the copolymer to a phase transition  
         condition which causes the copolymer to expand,  
         thereby releasing the template.

-17-


3. A method of Claim 2, further including the step of chromatographically separating the copolymer from the template.
- 5 4. A method of Claim 3, further including the steps of:
  - a) passing the copolymer through a gel-permeation chromatographic column which has the template bound thereto, whereby the copolymer which selectively binds the template can be retained  
10 on the gel;
  - b) exposing the gel and the copolymer to a phase-transition condition which causes at least a portion of the copolymer to bind to said template;
  - 15 c) washing said gel, whereby copolymer which is not bound to said template is removed from the gel;
  - d) exposing said gel and said bound copolymer to a phase transition condition which causes the  
20 bound copolymer to be released from the gel;  
and
  - e) washing said gel, whereby the released copolymer is removed from the gel.
- 25 5. A method of forming a multiple phase transition copolymer which can selectively catalyze a chemical

-18-


reaction converting a substrate into a product(s)  
comprising the steps of:

- a) forming a monomer solution which, upon  
polymerization, will form a copolymer that can  
exhibit phase transition at a plurality of  
distinct phase-transition conditions;
- b) combining the monomer solution with a template  
which, upon polymerization of the monomer  
solution, will cause the resulting copolymers  
to specifically catalyze the said substrate;
- c) exposing the combined monomer solution and  
template to conditions sufficient to cause the  
monomer solution to polymerize and form said  
copolymers; and
- d) exposing the copolymer to a phase-transition  
condition which cause the copolymer to expand,  
thereby releasing the template.


6. A method of Claim 5, further including the step of  
exposing the copolymer to a phase transition  
condition which cause the copolymer to shrink,  
thereby bringing back the copolymer to the original  
stable state and capable of catalyzing the  
substrate.




**FIG. 1A**




**FIG. 1B**




**FIG. 1C**




**FIG. 1D**



**FIG. 2A**






**FIG. 2B**



**FIG. 2C**

3/3



SUBSTITUTE SHEET (RULE 26)

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US94/05532

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :B01D 15/08  
US CL :210/635

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
U.S. : 210/635, 656, 198.2; 526/204, 205, 215, 216, 292.95, 303.1; 528/503

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
APS: molecular recognition, template, polymer

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US, A, 5,110,833 (MOSBACH) 05 May 1992, column 2, lines 24-49; column 3, lines 2-14; column 5, line 29 to column 6, line 6.	1-3, 5, 6
Y		-----
X	Accounts Chem. Res. Vol. 10, (RICH), "Three-Dimensional Structure and Biological Function of Transfer RNA" 1977, pages 388-396.	4
		1
A	PHYSICS TODAY, (CHAN et al.) "THE PROTEIN FOLDING PROBLEM", February 1993, Vol. 46, pages 24-32.	1-6

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

### \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be part of particular relevance

\*E\* earlier document published on or after the international filing date

\*L\* document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*Z\* document member of the same patent family

Date of the actual completion of the international search

04 AUGUST 1994

Date of mailing of the international search report

13 SEP 1994

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MARK NAGUMO

Telephone No. (703) 308-2351



**PThis Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)